



Celstran® PP-GF30-0501P10/13

Celanese Corporation - Polypropylene

Tuesday, November 5, 2019

General Information

Product Description

Material code according to ISO 1043-1: PP Heat stabilized polypropylene reinforced with 30 weight percent long glass fibers. The fibers are chemically coupled to the polypropylene matrix. The impact properties are enhanced. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding. Application field: Functional/structural parts for automotive

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Long Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Features	• Chemically Coupled • Good Isotropy • High Strength • Creep Resistant • Heat Stabilized • Low Temperature Impact Resistance • Good Impact Resistance • High Stiffness • Low Warpage
Uses	• Automotive Applications
RoHS Compliance	• Contact Manufacturer
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PP

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	899000	psi	ISO 527-2/1A
Tensile Stress (Break)	14500	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	%	ISO 527-2/1A/5
Flexural Modulus			ISO 178
73°F	870000	psi	
176°F	609000	psi	
Flexural Stress			ISO 178
73°F	21800	psi	
176°F	11600	psi	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	14	ft·lb/in ²	
73°F	14	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	38	ft·lb/in ²	
73°F	33	ft·lb/in ²	
Unnotched Izod Impact Strength (73°F)	26	ft·lb/in ²	ISO 180/1U

Celstran® PP-GF30-0501P10/13

Celanese Corporation - Polypropylene

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	316	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	252	°F	ISO 75-2/C
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.04 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	194 to 212	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	428 to 446	°F
Middle Temperature	446 to 464	°F
Front Temperature	464 to 482	°F
Nozzle Temperature	464 to 482	°F
Processing (Melt) Temp	446 to 518	°F
Mold Temperature	86 to 158	°F
Injection Rate	Slow	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 20 to 50°C
Zone4 temperature: 240 to 250°C
Hot runner temperature: 230 to 270°C

Notes

¹ Typical properties: these are not to be construed as specifications.