

Properties

MAS30, MAS30F

MS resin (UL94 HB)

UV stability

Properties	Test methods	Test conditions	Units	
Melt mass-flow rate	ISO 1133	220 deg C/10kg	g/10min	13
Mold shrinkage	ASTM D955	-	%	0.3-0.5
Tensile strength	ISO 527	-	MPa	70
Flexural strength	ISO 178	-	MPa	115
Flexural modulus	ISO 178	-	MPa	3400
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m ²	2
Notched Izod impact strength	ASTM D256	23 deg C/6.4mm	J/m	15
Rockwell hardness	ISO 2039	-	-	M80
Deflection temperature under load	ISO 75	1.80MPa	deg C	80
Deflection temperature under load	ASTM D648	1.82MPa/12.7mm	deg C	90
Ball pressure temperature	-	-	deg C	90
Coefficient of linear thermal expansion	ISO 11359	MD	X1E-5/deg C	7
Coefficient of linear thermal expansion	ISO 11359	TD	X1E-5/deg C	-
Flammability	UL94	-	-	HB
Water absorption	ISO 62	-	%	0.15
Density	ISO 1183	-	g/cm ³	1.13

Note

- Values are typical, not quality assured.
- UL recognition File No. of Daicel Polymer is E47773.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
3-5hrs 80-85deg C	210-230	210-230	190-210	170-190	70-90	10-20	40-60