

ECHO® RPPC20/2BK

Entec Polymers - Polypropylene Copolymer

Tuesday, November 5, 2019

General Information		
Product Description		
Copolymer Polypropylene		
General		
Material Status	Commercial: Active	
Availability	North America	
Features	Copolymer	
Appearance	Black	
Forms	• Pellets	

ASTM & ISO Properties 1			
Physical	Nominal Value Un	it Test Method	
Density / Specific Gravity	0.942	ASTM D792	
Melt Mass-Flow Rate (230°C/2.16 kg)	20 g/1	0 min ASTM D1238	
Impact	Nominal Value Un	it Test Method	
Notched Izod Impact (73°F)	2.0 ft·lk	o/in ASTM D256	

Notes

¹ Typical properties: these are not to be construed as specifications.