



ECHO® RPPC20/6BK

Entec Polymers - Polypropylene Copolymer

Tuesday, November 5, 2019

General Information

Product Description

Copolymer Polypropylene

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Copolymer
Appearance	• Black
Forms	• Pellets

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.942		ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	6.0	ft-lb/in	ASTM D256

Notes

¹ Typical properties: these are not to be construed as specifications.