



EnViramid® N2300THL BK

Ravago Manufacturing Americas - Polyamide 6

Monday, November 4, 2019

General Information

Product Description

Nylon 6, Impact Modified

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier
Recycled Content	• Yes
Features	• Impact Modified
RoHS Compliance	• RoHS Compliant
UL File Number	• E157012

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Molding Shrinkage - Flow (0.125 in)	1.5 to 1.9	%	ISO 294-4
Water Absorption (24 hr, 73°F)	1.6	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	7980	psi	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Modulus	305000	psi	ISO 178
Flexural Stress	10000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.8	ft-lb/in ²	ISO 179
Notched Izod Impact Strength	3.8	ft-lb/in ²	ISO 180

Notes

¹ Typical properties: these are not to be construed as specifications.