



Estane® 2103-70A TPU

Lubrizol Advanced Materials, Inc. - Thermoplastic Polyurethane Elastomer (Polyether)

Wednesday, November 6, 2019

General Information

Product Description

2103-70A is a thermoplastic polyurethane elastomer.

Feature: High MVTR

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Moisture Vapor Transmission		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.06		ASTM D792
Melt Mass-Flow Rate (224°C/8.7 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow	-3.0E-3 to 8.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow	4.0E-3 to 5.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 g, H-22 Wheel)	3.00	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (50% Strain, 0.126 in)	305	psi	ASTM D412
Tensile Stress (100% Strain, 0.126 in)	435	psi	ASTM D412
Tensile Stress (300% Strain, 0.126 in)	754	psi	ASTM D412
Tensile Strength (Break, 0.126 in)	3580	psi	ASTM D412
Tensile Elongation (Break, 0.126 in)	730	%	ASTM D412
Elongation Set After Break (0.126 in)	50	%	ASTM D412
Tear Strength ² (0.126 in)	380	lbf/in	ASTM D624
Compression Set			ASTM D395B
77°F, 22 hr	25	%	
158°F, 22 hr	75	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	72		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-92.2	°F	DSC
Vicat Softening Temperature	168	°F	ASTM D1525 ³
CLTE - Flow	9.7E-5	in/in/°F	ASTM D696

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180 to 199	°F
Processing (Melt) Temp	379 to 410	°F
Mold Temperature	61 to 140	°F

Estane® 2103-70A TPU

Lubrizol Advanced Materials, Inc. - Thermoplastic Polyurethane Elastomer (Polyether)

Injection Notes		
Air Dew Point: <-40°C		
Extrusion	Nominal Value	Unit
Drying Temperature	180 to 199	°F
Melt Temperature	370 to 399	°F
Extrusion Notes		
Air Dew Point: <-40°C		

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² Die C
- ³ Rate B (120°C/h), Loading 1 (10 N)