

## **HYLON® N7200HL**

## Ravago Manufacturing Americas - Polyamide 6/12 Copolymer

Monday, November 4, 2019

| General Information |                    |  |  |  |
|---------------------|--------------------|--|--|--|
| Product Description |                    |  |  |  |
| Nylon 6/12          |                    |  |  |  |
| General             |                    |  |  |  |
| Material Status     | Commercial: Active |  |  |  |
| Availability        | North America      |  |  |  |
| RoHS Compliance     | RoHS Compliant     |  |  |  |
| UL File Number      | • E157012          |  |  |  |

| ASTM & ISO Properties 1                           |               |           |             |  |
|---|---------------|-----------|-------------|--|
| Physical  | Nominal Value | Unit      | Test Method |  |
| Density   | 1.07          | g/cm³     | ISO 1183    |  |
| Molding Shrinkage - Flow (0.125 in)               | 1.1 to 1.5    | %         | ISO 294-4   |  |
| Mechanical  | Nominal Value | Unit      | Test Method |  |
| Tensile Stress (Break)                            | 7980          | psi       | ISO 527-2   |  |
| Tensile Strain (Break)                            | 50            | %         | ISO 527-2   |  |
| Flexural Modulus                                  | 203000        | psi       | ISO 178     |  |
| Flexural Stress                                   | 7540          | psi       | ISO 178     |  |
| Impact  | Nominal Value | Unit      | Test Method |  |
| Charpy Notched Impact Strength                    | 1.4           | ft·lb/in² | ISO 179     |  |
| Notched Izod Impact Strength                      | 1.4           | ft·lb/in² | ISO 180     |  |
| Thermal   | Nominal Value | Unit      | Test Method |  |
| Heat Deflection Temperature (264 psi, Unannealed) | 140           | °F        | ISO 75-2/A  |  |

## **Notes**



<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.