



## HYLOX® 9030

Ravago Manufacturing Americas - Polybutylene Terephthalate

Monday, November 4, 2019

### General Information

#### Product Description

PBT, 30% Glass Filled

#### General

|                        |                                     |
|------------------------|-------------------------------------|
| Material Status        | • Commercial: Active                |
| Availability           | • North America                     |
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight |
| RoHS Compliance        | • RoHS Compliant                    |
| UL File Number         | • E157012                           |

### ASTM & ISO Properties <sup>1</sup>

| Physical                                          | Nominal Value | Unit                  | Test Method |
|---------------------------------------------------|---------------|-----------------------|-------------|
| Density                                           | 1.53          | g/cm <sup>3</sup>     | ISO 1183    |
| Molding Shrinkage - Flow (0.125 in)               | 0.30 to 0.60  | %                     | ISO 294-4   |
| Mechanical                                        | Nominal Value | Unit                  | Test Method |
| Tensile Stress (Break)                            | 19000         | psi                   | ISO 527-2   |
| Tensile Strain (Break)                            | 3.0           | %                     | ISO 527-2   |
| Flexural Modulus                                  | 1.27E+6       | psi                   | ISO 178     |
| Flexural Stress                                   | 28600         | psi                   | ISO 178     |
| Impact                                            | Nominal Value | Unit                  | Test Method |
| Notched Izod Impact Strength                      | 3.3           | ft-lb/in <sup>2</sup> | ISO 180     |
| Thermal                                           | Nominal Value | Unit                  | Test Method |
| Heat Deflection Temperature (66 psi, Unannealed)  | 419           | °F                    | ISO 75-2/B  |
| Heat Deflection Temperature (264 psi, Unannealed) | 410           | °F                    | ISO 75-2/A  |
| Flammability                                      | Nominal Value | Unit                  | Test Method |
| Flame Rating (0.028 in)                           | HB            |                       | UL 94       |

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.