



Hostaform® MT® SlideX™ 1203

Celanese Corporation - Acetal (POM) Copolymer

Sunday, November 3, 2019

General Information

Product Description

Hostaform® MT® SlideX™ 1203 is a standard flow injection molding grade with tribological modification designed for use in demanding applications that require prevention of audible noise caused by stick-slip phenomenon and low friction and wear against plastics and metals.

Hostaform® MT SlideX™ 1203 is a special grade developed for medical industry applications and complies with:

- CFR 21 (177.2470) of the Food and Drug Administration (FDA) and is listed in the Drug Master File (DMF 11559) and the Device Master File (MAF 1079)
- the corresponding EU and national registry regulatory requirements
- biocompatibility in tests corresponding to USP <88> Class VI/ISO 10993
- low residual monomers
- no animal-derived constituents

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Biocompatible • Low Friction	• No Animal Derived Components • Wear Resistant	
Uses	• Medical/Healthcare Applications		
Agency Ratings	• DMF 11559 • FDA 21 CFR 177.2470	• ISO 10993 • MAF 1079	• USP Class VI
RoHS Compliance	• Contact Manufacturer		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	13	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.6	%	
Flow	2.0	%	
Water Absorption (Saturation, 73°F)	0.60	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	384000	psi	ISO 527-2/1A
Tensile Stress (Yield)	8410	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	12	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	45	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	363000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.9	ft-lb/in ²	
73°F	2.9	ft-lb/in ²	

Hostaform® MT® SlideX™ 1203

Celanese Corporation - Acetal (POM) Copolymer

Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	71	ft-lb/in ²	
73°F	76	ft-lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness ²	20000	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	199	°F	ISO 75-2/A
Vicat Softening Temperature	304	°F	ISO 306/B50
Melting Temperature ³	338	°F	ISO 11357-3
CLTE - Flow	7.2E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	7.2E-5	in/in/°F	ISO 11359-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Hopper Temperature	68 to 86	°F
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	374 to 392	°F
Nozzle Temperature	374 to 410	°F
Processing (Melt) Temp	374 to 410	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow-Moderate	
Back Pressure	< 580	psi

Injection Notes

Feeding zone temperature: 60 to 80°C
 Zone4 temperature: 190 to 210°C
 Hot runner temperature: 190 to 210°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 30s

³ 10°C/min