



Hostaform® S 27063

Celanese Corporation - Acetal (POM) Copolymer

Sunday, November 3, 2019

General Information

Product Description

Chemical abbreviation according to ISO 1043-1: POM-HI, Molding compound ISO 9988- POM-K, M-GNPR, 05-001 POM copolymer, modified Easy flowing elastomer-containing injection molding type based on HOSTAFORM C 27021; with higher impact strength and slightly lower hardness, rigidity and chemical resistance than the basic type; high resistance to thermal and oxidative degradation. UL-registration in natural and a thickness more than 1.57 mm as UL 94 HB. Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness more than 1 mm thickness. Ranges of applications: For thin-walled molded parts with higher energy-absorbing capacity UL = Underwriters Laboratories (USA) FMVSS = Federal Motor Vehicle Safety Standard (USA)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Flow	• Good Impact Resistance	• High Energy Absorption
Uses	• Thin-walled Parts		
RoHS Compliance	• Contact Manufacturer		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• POM-HI		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	20	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	1.9	%	
Water Absorption (Saturation, 73°F)	0.65	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	319000	psi	ISO 527-2/1A
Tensile Stress (Yield)	7830	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	30	%	ISO 527-2/1A/50
Tensile Creep Modulus (1 hr)	268000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	152000	psi	ISO 899-1
Flexural Modulus (73°F)	305000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.9	ft-lb/in ²	
73°F	4.3	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	43	ft-lb/in ²	
73°F	67	ft-lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness ²	16700	psi	ISO 2039-1

Hostaform® S 27063

Celanese Corporation - Acetal (POM) Copolymer

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	183	°F	ISO 75-2/A
Vicat Softening Temperature	284	°F	ISO 306/B50
Melting Temperature ³	331	°F	ISO 11357-3
CLTE - Flow	6.7E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+13	ohms·cm	IEC 60093
Electric Strength	710	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.20		
1 MHz	4.20		
Dissipation Factor			IEC 60250
100 Hz	5.0E-3		
1 MHz	0.015		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	HB		
0.12 in	HB		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Hopper Temperature	68 to 86	°F
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	374 to 392	°F
Nozzle Temperature	374 to 392	°F
Processing (Melt) Temp	374 to 392	°F
Mold Temperature	140 to 158	°F
Injection Rate	Slow-Moderate	
Back Pressure	< 290	psi

Injection Notes

Feeding zone temperature: 60 to 80°C
Zone4 temperature: 190 to 200°C
Hot runner temperature: 190 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 30s

³ 10°C/min