



INEOS PP N02G-00

INEOS Olefins & Polymers USA - Polypropylene Impact Copolymer

Tuesday, November 5, 2019

General Information

Product Description

N02G-00 is a low melt flow rate, high-impact copolymer polypropylene for sheet extrusion and thick wall injection molding applications. It offers a superior balance of stiffness and impact strength as compared to competitive impact copolymers of similar melt flow rate range. Typical applications include appliances, automotive, compounding, consumer products, housewares, and rigid packaging. Benefits include enhanced impact and stiffness. This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.

General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Food Contact Acceptable • High Impact Resistance	• Impact Copolymer • Low Flow	
Uses	• Appliances • Automotive Applications • Compounding	• Consumer Applications • Household Goods • Rigid Packaging	• Sheet • Thick-walled Parts
Agency Ratings	• EC 1907/2006 (REACH)	• FDA 21 CFR 177.1520	
RoHS Compliance	• Contact Manufacturer		
Forms	• Pellets		
Processing Method	• Injection Molding	• Sheet Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.900		ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, Injection Molded)	3700	psi	ASTM D638
Tensile Strength ² (Break, Injection Molded)	2600	psi	ASTM D638
Tensile Elongation ² (Yield, Injection Molded)	6.7	%	ASTM D638
Tensile Elongation ² (Break, Injection Molded)	320	%	ASTM D638
Flexural Modulus - 1% Secant (Injection Molded)	173000	psi	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-4°F, Injection Molded	1.6	ft-lb/in	
73°F, Injection Molded	No Break		
Notched Izod Impact (Area) (-4°F, Injection Molded)	3.90	ft-lb/in ²	ASTM D256
Instrumented Dart Impact			ASTM D3763
-4°F, Injection Molded, Ductile Failure	No Break		
73°F, Injection Molded, Ductile Failure	No Break		
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	86		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi, Unannealed, Injection Molded	202	°F	
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, Injection Molded	126	°F	

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

INEOS PP N02G-00

INEOS Olefins & Polymers USA - Polypropylene Impact Copolymer

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	304	°F	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (60°, Injection Molded)	69		ASTM D2457

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min