



Ravago Compounds PP-4290

Ravago Manufacturing Americas - Polypropylene Impact Copolymer

Tuesday, November 5, 2019

General Information

Product Description

Key Features:

- Polypropylene Impact Copolymer
- UL Recognition listing - UL-94 V0
- Designed for Injection molded applications
- Good balance of processability and physical properties

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Flame Retardant • Good Processability • Impact Copolymer
UL File Number	• E141240
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.01		ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	17	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 73°F)	3350	psi	ASTM D638
Tensile Elongation (Yield, 73°F)	10	%	ASTM D638
Flexural Modulus - Tangent ²	160000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.5	ft-lb/in	ASTM D256
Gardner Impact ³ (73°F)	> 320	in-lb	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Annealed)	220	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94
Oxygen Index	29	%	ASTM D2863

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	160 to 200	°F
Drying Time	0.0 to 8.0	hr
Rear Temperature	350 to 420	°F
Middle Temperature	350 to 420	°F
Front Temperature	340 to 420	°F
Nozzle Temperature	360 to 420	°F
Processing (Melt) Temp	< 500	°F
Mold Temperature	80 to 140	°F
Back Pressure	0.00 to 100	psi
Screw Speed	50 to 150	rpm

Ravago Compounds PP-4290

Ravago Manufacturing Americas - Polypropylene Impact Copolymer

Injection Notes

Hot Runner: 380 to 450°F

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.050 in/min

³ Geometry GB