



TRIEX® 3030U

Samyang Corporation - Polycarbonate

Tuesday, November 5, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• UV Stabilizer		
Features	• Good Dimensional Stability • Good Electrical Properties • Good Flow	• Good Weather Resistance • High Viscosity • Low Moisture Absorption	• Low Temperature Impact Resistance
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (300°C/1.2 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.118 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	10200	psi	ASTM D638
Tensile Strength (Yield)	10200	psi	ASTM D638
Tensile Elongation (Break)	130	%	ASTM D638
Flexural Modulus	333000	psi	ASTM D790
Flexural Strength (Yield)	13400	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	19	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	273	°F	ASTM D648
CLTE - Flow	2.8E-5 to 3.9E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	ASTM D257
Dielectric Strength	760	V/mil	ASTM D149
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-2		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248	°F
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	455 to 500	°F
Middle Temperature	482 to 527	°F
Front Temperature	509 to 554	°F
Nozzle Temperature	509 to 572	°F

TRIEX® 3030U

Samyang Corporation - Polycarbonate

Injection	Nominal Value	Unit
Processing (Melt) Temp	509 to 572	°F
Mold Temperature	149 to 221	°F
Screw Speed	40 to 70	rpm
Vent Depth	7.9E-4 to 0.031	in

Notes

¹ Typical properties: these are not to be construed as specifications.