



Toppyl SP 2001 B

LyondellBasell Industries - Polyolefin

Tuesday, November 5, 2019

General Information

Product Description

Toppyl SP 2001 B is a fully formulated seal peel solution especially developed for the blown ?lm technology.

This product has been designed to offer a peelable seal to PE substrates or to seal & peel against itself and is suitable for non-sterilisable applications.

Toppyl SP 2001 B is a solution created to replace completely the sealing layer in a coextruded ?lm.

It provides a constant easy-opening force over a wide sealing temperature window and is readily processable on conventional equipment in both mono and co-extruded structures.

EU and FDA compliance information about this product can be found in separate product documentation.

This product is not intended for use in medical and pharmaceutical applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Medium Antiblock		• Medium Slip
Features	• Broad Seal Range • Good Heat Seal • Good Melt Strength	• Good Tear Strength • Medium Antiblocking • Medium Slip	• Semi Crystalline
Uses	• Film		
Agency Ratings	• EU Unspecified Rating	• FDA Unspecified Rating	
Processing Method	• Blown Film	• Coextrusion	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	0.80	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic)	0.25		ASTM D1894
Films	Nominal Value	Unit	Test Method
Secant Modulus - MD	29000	psi	ASTM D882
Tensile Strength - MD (Yield)	1740	psi	ASTM D882
Tensile Strength - MD (Break)	4060	psi	ASTM D882
Tensile Elongation - MD (Break)	580	%	ASTM D882
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	203	°F	ISO 306/A50
Melting Temperature	235	°F	DSC

Additional Information

Recommended processing temperatures: 170°C to 230°C. In cases were higher temperatures are required please contact your appropriate technical contact for support.

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Topyl SP 2001 B

LyondellBasell Industries - Polyolefin

Notes

¹ Typical properties: these are not to be construed as specifications.