



Ultradur® B 4441 G5

BASF Corporation - Polybutylene Terephthalate

Monday, November 4, 2019

General Information

Product Description

Ultradur B 4441 G5 is a 25% glass reinforced injection molding PBT optimized for glow wire requirements. For parts requiring enhanced fire resistance. (Halogen and Antimony free)

Applications

Typical applications include components for household appliances, connectors, and power switches.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Features	• Antimony Free • Flame Retardant • Halogen Free
Uses	• Appliance Components • Connectors • Switches
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/2.16 kg)	15	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.2	%	
Flow	0.44	%	
Water Absorption (Saturation, 73°F)	0.40	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Viscosity Number (Reduced Viscosity)	105.0	ml/g	ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.42E+6	psi	ISO 527-2
Tensile Stress (Break, 73°F)	16000	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.3	%	ISO 527-2
Flexural Modulus (73°F)	1.45E+6	psi	ISO 178
Flexural Stress (73°F)	26100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.3	ft·lb/in ²	ISO 179
Charpy Unnotched Impact Strength			ISO 179
-22°F	22	ft·lb/in ²	
73°F	21	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	428	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	410	°F	ISO 75-2/A
Melting Temperature (DSC)	433	°F	ISO 3146
RTI Elec (0.06 in)	284	°F	UL 746

Ultradur® B 4441 G5

BASF Corporation - Polybutylene Terephthalate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant (1 MHz)	3.60		IEC 60250
Dissipation Factor (1 MHz)	0.014		IEC 60250
Comparative Tracking Index	525	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.016 in		V-0	
0.06 in		5VA	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	482 to 518	°F
Mold Temperature	140 to 212	°F
Injection Pressure	500 to 1500	psi
Injection Rate	Fast	
Back Pressure	< 145	psi

Notes

¹ Typical properties: these are not to be construed as specifications.