



Ultramid® B3WG6 BK00564

BASF Corporation - Polyamide 6

Monday, November 4, 2019

General Information

Product Description

Ultramid B3WG6 BK00564 is a 30% glass fiber reinforced, pigmented black, heat stabilized injection molding PA6 grade.

Applications

Typical applications include automotive manifolds and pedals.

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized • Oil Resistant
Uses	• Automotive Applications
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• FORD WSK-M4D664-A • FORD WSK-M4D664-A2 • GM GMW3029P-PA6-GF30H • GM GMW3029P-PA6-GF30H Color: Black • GM GMW3029P-PA6-GF30H Color: Natural • IMDS ID 40069704 • PSA Peugeot-Citroën SPA X62 4519 • PSA Peugeot-Citroën SPA X62 4522
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density / Specific Gravity	1.36	--		ASTM D792
Density	1.36	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)				ISO 1133
275°C/5.0 kg	40	--	cm ³ /10min	
Molding Shrinkage - Flow (0.125 in)	3.0E-3	--	in/in	
Water Absorption (Saturation)	6.6	--	%	ASTM D570
Water Absorption				ISO 62
Saturation, 73°F	6.6	--	%	
Water Absorption				ASTM D570
Equilibrium, 50% RH	2.1	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	2.1	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.38E+6	870000	psi	ISO 527-2
Tensile Strength (Break, 73°F)	26100	16000	psi	ASTM D638
Tensile Stress (Break, 73°F)	26100	15200	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	6.0	%	ISO 527-2
Flexural Modulus (73°F)	1.20E+6	725000	psi	ISO 178

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Ultramid® B3WG6 BK00564

BASF Corporation - Polyamide 6

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-22°F	4.3	--	ft·lb/in ²	
73°F	5.7	9.5	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179
-22°F	31	--	ft·lb/in ²	
73°F	38	45	ft·lb/in ²	
Notched Izod Impact				ASTM D256
-40°F	2.0	--	ft·lb/in	
73°F	2.8	4.8	ft·lb/in	
Notched Izod Impact Strength				ISO 180
73°F	5.7	--	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
66 psi, Unannealed	428	--	°F	
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	428	--	°F	
Deflection Temperature Under Load				ASTM D648
264 psi, Unannealed	410	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	401	--	°F	
Peak Melting Temperature	428	--	°F	ASTM D3418
Melting Temperature (DSC)	428	--	°F	ISO 3146

Processing Information

Injection	Dry	Unit
Drying Temperature	181	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	518 to 563	°F
Mold Temperature	176 to 203	°F
Injection Pressure	508 to 1810	psi
Injection Rate	Fast	

Notes

¹ Typical properties: these are not to be construed as specifications.