



Vydyne® R533H NT

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Vydyne R533H NT is 33% glass-fiber reinforced, heat-stabilized PA66 resin. Available in natural, it is specifically designed to maximize the retention of physical properties when exposed to anti-freeze solutions at elevated temperatures. This product is lubricated for improved machine feed and flow.

Glass-reinforced Vydyne resins provide higher heat distortion temperature, resistance to creep and better dimensional stability when compared with unreinforced PA66. These products have good chemical resistance to a broad range of chemicals including gasoline, hydraulic fluids and most solvents.

Vydyne R533H NT resin is heat-stabilized to minimize oxidative degradation of the polymer when exposed to elevated temperatures in service. This product provides improved retention of physical properties under exposure to long-term heat. Also, Vydyne R533H NT resin has excellent knit-line strength and fatigue resistance, which is essential for cycle testing with anti-freeze solutions.

Typical Applications/End Uses:

Vydyne R533H NT resin has been used for many under-the-hood automotive applications, motor housings for power tools and garden appliances. This resin has also been used in miscellaneous brackets, gears and clips that require high rigidity and strength.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight		
Additive	• Heat Stabilizer	• Lubricant	
Features	• Good Mold Release • Heat Stabilized	• High Flow • High Rigidity	• High Strength • Lubricated
Uses	• Automotive Under the Hood • Gears	• Housings • Power/Other Tools	• Transmission Applications
Agency Ratings	• ASTM D4066 PA012G35 • ASTM D6779 PA012G35	• EC 1935/2004 • EU 10/2011	• EU 2023/2006 • FDA 21 CFR 177.1500
Automotive Specifications	• CHRYSLER MS-DB-41 CPN2043 • DELPHI M-4692V • FORD ESE-M4D287-A	• FORD ESE-M4D287-B • FORD WSK-M4D663-A • GM GMP.PA66.013	• GM GMP.PA66.054 • GM GMW15702-110057
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.40	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.90	--	%	
Flow : 73°F, 0.0787 in	0.40	--	%	
Water Absorption (24 hr, 73°F)	0.80	--	%	ISO 62
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	1.7	--	%	

Vydyne® R533H NT

Ascend Performance Materials Operations LLC - Polyamide 66

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.54E+6	1.15E+6	psi	ISO 527-2
Tensile Stress (Break, 73°F)	29700	21000	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	5.0	%	ISO 527-2
Flexural Modulus (73°F)	1.48E+6	943000	psi	ISO 178
Flexural Stress (73°F)	42000	29000	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	4.8	5.7	ft·lb/in²	
73°F	5.2	6.7	ft·lb/in²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	33	40	ft·lb/in²	
73°F	38	43	ft·lb/in²	
Notched Izod Impact Strength				ISO 180
-22°F	4.8	5.7	ft·lb/in²	
73°F	5.7	6.7	ft·lb/in²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	500	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	482	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	1.2E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.9E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.030 in	284	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
RTI Imp				UL 746
0.030 in	257	--	°F	
0.06 in	257	--	°F	
0.12 in	257	--	°F	
RTI Str				UL 746
0.030 in	284	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+13	--	ohms·cm	IEC 60093
Dielectric Strength (0.0394 in)	510	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 6	--		ASTM D495
Comparative Tracking Index				IEC 60112
0.118 in	250 to 399	--	V	
High Amp Arc Ignition (HAI)				UL 746
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746

Vydyne® R533H NT

Ascend Performance Materials Operations LLC - Polyamide 66

Electrical	Dry	Conditioned	Unit	Test Method
Hot-wire Ignition (HWI)				UL 746
0.030 in	PLC 4	--		
0.06 in	PLC 3	--		
0.12 in	PLC 4	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.030 in	HB	--		
0.06 in	HB	--		
0.12 in	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 in	1340	--	°F	
0.06 in	1290	--	°F	
0.12 in	1610	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 in	1380	--	°F	
0.06 in	1340	--	°F	
0.12 in	1380	--	°F	

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Suggested Max Regrind	25	%
Rear Temperature	536 to 590	°F
Middle Temperature	536 to 590	°F
Front Temperature	536 to 590	°F
Nozzle Temperature	536 to 590	°F
Processing (Melt) Temp	545 to 581	°F
Mold Temperature	149 to 203	°F

Notes

¹ Typical properties: these are not to be construed as specifications.