

Arnite® T08 200 (extrusion)
 Envalior - Polybutylene Terephthalate

General Information

Product Description

High Viscosity, Injection Molding, Extrusion, Food Contact Quality

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Food Contact Acceptable	• High Viscosity	
Processing Method	• Extrusion	• Injection Molding	
Resin ID	• PBT		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	10	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 73°F)	0.45	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.18	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	370000	psi	ISO 527-1
Tensile Stress (Yield)	7980	psi	ISO 527-2
Tensile Strain (Yield)	3.5	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.9	ft-lb/in ²	
73°F	2.9	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	No Break		
73°F	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	338	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	131	°F	ISO 75-2/A
Melting Temperature ²	437	°F	ISO 11357-3
CLTE - Flow	5.0E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	5.0E-5	in/in/°F	ISO 11359-2
Effective Thermal Diffusivity	7.21E-5	in ² /s	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Electric Strength	690	V/mil	IEC 60243-1
Relative Permittivity			IEC 62631-2-1
100 Hz	3.50		
1 MHz	3.20		
Dissipation Factor			IEC 62631-2-1
100 Hz	2.0E-3		
1 MHz	0.020		
Comparative Tracking Index	600	V	IEC 60112
Fill Analysis	Nominal Value	Unit	Test Method
Melt Density	1.04	g/cm ³	



Melt Specific Heat	0.540 Btu/lb/°F		
Melt Thermal Conductivity	0.76 Btu·in/hr/ft ² /°F		ASTM E1461
Additional Information	Nominal Value	Unit	Test Method
RSV - m-cresol, 1g/100ml	2.40		Internal Method

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

