

**Arnite® TV6 241 SN**

Envalior - Polybutylene Terephthalate

## General Information

**Product Description**

20% Glass Fiber Reinforced, Flame Retardant

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Features	• Flame Retardant
Processing Method	• Injection Molding
Resin ID	• PBT-GF20 FR(17)

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.62	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.2	%	
Flow	0.60	%	
Water Absorption (Saturation, 73°F)	0.40	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.23E+6	psi	ISO 527-1
Tensile Stress (Break)	17400	psi	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.3	ft·lb/in <sup>2</sup>	
73°F	4.3	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	24	ft·lb/in <sup>2</sup>	
73°F	24	ft·lb/in <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	428	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	410	°F	ISO 75-2/A
Melting Temperature <sup>2</sup>	437	°F	ISO 11357-3
CLTE - Flow	2.2E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	4.4E-5	in/in/°F	ISO 11359-2
RTI Elec (0.030 in)	284	°F	UL 746B
RTI Imp			UL 746B
0.030 in	266	°F	
0.12 in	284	°F	
RTI Str (0.030 in)	284	°F	UL 746B
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Relative Permittivity			IEC 62631-2-1
100 Hz	3.20		
1 MHz	3.20		
Dissipation Factor			IEC 62631-2-1



100 Hz	1.0E-3		
1 MHz	0.014		
Comparative Tracking Index (CTI)	PLC 2		UL 746A
Comparative Tracking Index	250 V		IEC 60112
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating			UL 94
0.06 in		V-0	
0.12 in		V-0	
Flammability Classification			IEC 60695-11-10, -20
0.06 in		V-0	
0.12 in		V-0	
0.030 in		V-2	

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 10°C/min

