

AuroraGuard™ 2002V

Aurora Material Solutions, LLC - Acrylonitrile Butadiene Styrene

General Information

Product Description

General Purpose ABS

Formerly known as EnCore 2002V

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• General Purpose		
Uses	• General Purpose		
Appearance	• Black		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.05		ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 8.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	280000	psi	ASTM D638
Tensile Strength (Yield)	5000	psi	ASTM D638
Tensile Elongation (Break)	4.4	%	ASTM D638
Flexural Modulus	290000	psi	ASTM D790
Flexural Strength	6000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	2.0	ft-lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180 to 200	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	370 to 450	°F
Middle Temperature	400 to 475	°F
Front Temperature	425 to 500	°F
Nozzle Temperature	425 to 525	°F
Processing (Melt) Temp	425 to 525	°F
Mold Temperature	120 to 170	°F
Back Pressure	25.0 to 100	psi
Screw Speed	25 to 75	rpm

Injection Notes

Maximum Drying Time 7 hr

Notes

¹ Typical properties: these are not to be construed as specifications.

