

AuroraGuard™ 2205P

Aurora Material Solutions, LLC - Acrylonitrile Butadiene Styrene Alloy

General Information

Product Description

High Heat, high Impact Paintable, Platable, ABS Alloy

Formerly known as EnCore 2205P

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Heat Resistance	• High Impact Resistance	• Paintable
Uses	• Automotive Applications	• Business Equipment	• General Purpose
Appearance	• Black • Colors Available	• Natural Color • Opaque	
Processing Method	• Injection Molding	• Profile Extrusion	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.05		ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6530	psi	ASTM D638
Flexural Modulus	375000	psi	ASTM D790
Flexural Strength	11000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	5.0	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	190	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	171	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		HB	
0.13 in		HB	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180 to 200	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	370 to 450	°F
Middle Temperature	400 to 475	°F
Front Temperature	425 to 500	°F
Nozzle Temperature	425 to 525	°F
Processing (Melt) Temp	425 to 525	°F
Mold Temperature	120 to 170	°F
Back Pressure	25.0 to 100	psi
Screw Speed	25 to 75	rpm

Injection Notes

Maximum Drying Time: 7.0 hrs

