

AuroraGuard™ 630GFHSQ

Aurora Material Solutions, LLC - Polyamide 6

General Information

Product Description

30% Glass Filled, Heat Stabilized Nylon 6, with outstanding surface appearance. For use in highly cosmetic applications where appearance and strength are critical.

Formerly known as EnLon 630GFHSQ

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Good Strength	• Heat Stabilized	• Pleasing Surface Appearance
Uses	• Automotive Applications	• Material Handling	
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Molding Shrinkage - Flow (0.126 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24900	psi	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	31000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	2.0	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	405	°F	ASTM D648
Additional Information	Nominal Value	Unit	Test Method
Filler Content	30	%	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	470 to 520	°F
Middle Temperature	480 to 530	°F
Front Temperature	490 to 540	°F
Nozzle Temperature	490 to 540	°F
Processing (Melt) Temp	490 to 540	°F
Mold Temperature	130 to 200	°F
Injection Notes		
Maximum Drying Time	4 hrs	

