

AuroraGuard™ GEP 6HSL

Aurora Material Solutions, LLC - Polyamide 6

General Information

Product Description

Reprocessed Nylon 6, Heat Stabilized with Internal and External Lubricants

Formerly known as EnLon GEP 6HSL

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Heat Stabilizer • Lubricant		
Features	• Heat Stabilized • Lubricated		
Uses	• Automotive Applications	• Industrial Applications	• Material Handling
Appearance	• Black		
Forms	• Pellets, Reprocessed		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11500	psi	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	420000	psi	ASTM D790
Flexural Strength	16000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.99	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	145	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	470 to 520	°F
Middle Temperature	480 to 530	°F
Front Temperature	490 to 540	°F
Nozzle Temperature	490 to 540	°F
Processing (Melt) Temp	490 to 530	°F
Mold Temperature	130 to 200	°F
Injection Notes		
Maximum Drying Time 4 hrs		

