

ColorFast® FRA205UV*Americhem - Acrylonitrile Butadiene Styrene***General Information****Product Description**

FRA205UV is a flame-retardant high gloss ABS with superior UV stability and a flame rating of V-0/1.5mm.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Flame Retardant	• UV Stabilizer	
Features	• Excellent Colorability	• Flame Retardant	• UV Stabilized
Uses	• Consumer Applications • Household Goods	• Industrial Applications • Industrial Parts	• Outdoor Applications
UL File Number	• E178307		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.28		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	5600	psi	ASTM D638
Tensile Elongation ² (Break)	12	%	ASTM D638
Flexural Modulus ²	340000	psi	ASTM D790
Flexural Strength ²	8400	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	4.0	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed, 0.250 in)	163	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	160 to 180	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Suggested Shot Size	50 to 70	%
Rear Temperature	340 to 360	°F
Middle Temperature	390 to 410	°F
Front Temperature	410 to 430	°F
Nozzle Temperature	380 to 430	°F
Processing (Melt) Temp	380 to 450	°F
Mold Temperature	160 to 180	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm
Vent Depth	1.5E-3 to 2.0E-3	in



Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min

