

DURANEX® 361SA

Polyplastics - Acrylonitrile Butadiene Styrene + PBT

General Information

Product Description

Low Warpage, SA Series

GF Reinforced, Low Density, High Sliding

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Low Friction • Low Density • Low Warpage
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT+ABS-GF15 FR(17)<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	13100	psi	ISO 527-2
Tensile Strain (Break)	2.1	%	ISO 527-2
Flexural Modulus	827000	psi	ISO 178
Flexural Stress	18700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	75		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	257	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	2.2E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+16	ohms·cm	IEC 60093
Electric Strength (0.118 in)	510	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number	ED3002		

Notes

¹ Typical properties: these are not to be construed as specifications.

