

DURANEX® 711SA

Polyplastics - Acrylonitrile Butadiene Styrene + PBT

General Information

Product Description

Low Warpage, SA Series

GF Reinforced, Low Density, High Sliding

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Low Density • Low Friction • Low Warpage
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT+ABS-(GF+PS)30<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	13500	psi	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	1.11E+6	psi	ISO 178
Flexural Stress	18900	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.5	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	356	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	1.7E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	3.3E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Electric Strength (0.118 in)	660	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number	EF2001/ED3002		

Notes

¹ Typical properties: these are not to be construed as specifications.

