

Electrafil® ABS CF20 BK

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.5E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.14	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	16000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.73E+6	psi	ASTM D790
Flexural Strength	22000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.1	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	5.0	ft·lb/in	ASTM D4812
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	235	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	220	°F	ASTM D648
CLTE - Flow	1.7E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 to 1.0E+4	ohms	ASTM D257
Volume Resistivity	10 to 1.0E+3	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	170 to 190	°F
Drying Time	2.0 to 16	hr
Rear Temperature	420 to 450	°F
Middle Temperature	430 to 460	°F
Front Temperature	410 to 430	°F
Nozzle Temperature	390 to 430	°F
Processing (Melt) Temp	450 to 500	°F
Mold Temperature	160 to 190	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

