

Electrafil® HIPS E

Techmer Polymer Modifiers - *High Impact Polystyrene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Antistatic
Features	• Antistatic • Conductive
Appearance	• Colors Available • Natural Color
Forms	• Pellets
Processing Method	• Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.07		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	7.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29000	psi	ASTM D638
Tensile Elongation (Yield)	30	%	ASTM D638
Flexural Modulus	210000	psi	ASTM D790
Flexural Strength	4100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.0	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	60		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	205	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	185	°F	ASTM D648
CLTE - Flow	3.5E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8 to 1.0E+11	ohms	ASTM D257
Volume Resistivity	1.0E+8 to 1.0E+11	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

