

Electrafil® J-1200/CF/20

Techmer Polymer Modifiers - Acrylonitrile Butadiene Styrene

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight		
Features	• Antistatic	• Electrically Conductive	
Uses	• Automotive Electronics • Bushings	• Business Equipment • Conveyor Parts	• Packaging
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-4	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	2.00E+6	psi	ASTM D638
Tensile Strength (Break, 73°F)	14000	psi	ASTM D638
Tensile Elongation (Break, 73°F)	1.0	%	ASTM D638
Flexural Modulus (73°F)	1.80E+6	psi	ASTM D790
Flexural Strength (Break, 73°F)	20000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.2	ft·lb/in	ASTM D256
Unnotched Izod Impact (73°F, 0.125 in)	4.0	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	220	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	215	°F	ASTM D648
CLTE - Flow	1.2E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	50	ohms	ASTM D257
Volume Resistivity	5.0	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Additional Information

Surface Resistivity, ASTM D257: 10-100 ohms/sq
Volume Resistivity, ASTM C611: 1-10 ohm-cm

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	170 to 190	°F
Drying Time	2.0 to 16	hr
Rear Temperature	420 to 450	°F
Middle Temperature	430 to 460	°F
Front Temperature	410 to 430	°F
Nozzle Temperature	390 to 430	°F
Processing (Melt) T	450 to 500	°F



Mold Temperature	160 to 190 °F
Notes	
¹ Typical properties: these are not to be construed as specifications.	

