

HiFill® ABS GF20 GY071

 Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Appearance	• Grey
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800000	psi	ASTM D638
Tensile Strength (Yield)	9200	psi	ASTM D638
Tensile Elongation (Break)	1.8	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.90	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	455 to 480	°F
Middle Temperature	465 to 490	°F
Front Temperature	475 to 500	°F
Nozzle Temperature	475 to 500	°F
Processing (Melt) Temp	475 to 525	°F
Mold Temperature	110 to 150	°F
Injection Rate	Slow	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

Notes
¹ Typical properties: these are not to be construed as specifications.
