

HiFill FR® CONC HDPE FR

Techmer Polymer Modifiers - *High Density Polyethylene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Flame Retardant
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	2900	psi	ASTM D638
Tensile Elongation (Yield)	200	%	ASTM D638
Flexural Modulus	140000	psi	ASTM D790
Flexural Strength	4100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.0	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

