

HiFill FR® PA12 IM FR

Techmer Polymer Modifiers - *Polyamide 12*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier • Lubricant
Features	• Flame Retardant • Impact Modified • Lubricated
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.25	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7500	psi	ASTM D638
Tensile Elongation (Yield)	50	%	ASTM D638
Flexural Modulus	120000	psi	ASTM D790
Flexural Strength	10000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	10	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	55		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	200	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	140	°F	ASTM D648
CLTE - Flow	7.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	450	V/mil	ASTM D149

Notes

¹ Typical properties: these are not to be construed as specifications.

