

HiFill® HDPE 2443 3DP BK

Techmer Polymer Modifiers - *High Density Polyethylene*

General Information

Product Description

HiFill® HDPE 2443 3DP BK is a specially formulated, black colored, and compounded thermoplastic material designed for general purpose additive manufacturing applications. This product has been optimized for maximum printability in additive manufacturing.

General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Additive Manufacturing (3D Printing)
Appearance	• Black

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.960		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3000	psi	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Flexural Modulus	100000	psi	ASTM D790
Flexural Strength	3000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.0	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	122	°F	ASTM D648
Additional Information	Nominal Value	Unit	Test Method
Recommended Print Bed	HDPE sheet		
Recommended Print Bed Temperature	170 to 180	°F	

Processing Information

Extrusion	Nominal Value	Unit
Drying Temperature	150	°F
Drying Time	1.0 to 2.0	hr
Cylinder Zone 1 Temp.	320 to 350	°F
Cylinder Zone 2 Temp.	330 to 360	°F
Cylinder Zone 3 Temp.	340 to 370	°F
Cylinder Zone 4 Temp.	350 to 380	°F
Melt Temperature	360 to 400	°F
Die Temperature	360 to 400	°F

Extrusion Notes

If drying for longer than 6 hours, recommend reducing the temperature to 100°F in a dessiccant dryer to avoid degradation of the material. HDPE is not a hygroscopic resin and not expected to pickup significant moisture.

Notes

¹ Typical properties: these are not to be construed as specifications.

