

HiFill® HDPE GF10 CC

Techmer Polymer Modifiers - *High Density Polyethylene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight
Features	• Chemically Coupled
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.01		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	7000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	230000	psi	ASTM D790
Flexural Strength	10000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.9	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	80		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	230	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	190	°F	ASTM D648
CLTE - Flow	4.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	300	V/mil	ASTM D149

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	170	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	450 to 500	°F
Middle Temperature	450 to 500	°F
Front Temperature	450 to 500	°F
Processing (Melt) Temp	425 to 475	°F
Mold Temperature	80 to 120	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

