

HiFill® PA11

Techmer Polymer Modifiers - *Polyamide 11*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Medium Viscosity
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.03		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9500	psi	ASTM D638
Tensile Elongation (Yield)	10	%	ASTM D638
Flexural Modulus	160000	psi	ASTM D790
Flexural Strength	11000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.4	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	113	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	75.0	°F	ASTM D648
CLTE - Flow	7.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	450	V/mil	ASTM D149
Additional Information	Nominal Value	Unit	Test Method
TPCI #	6486106		

Notes

¹ Typical properties: these are not to be construed as specifications.

