

InStruc® ABSGF20EX

Americhem - Acrylonitrile Butadiene Styrene

General Information

Product Description

20% GLASS REINFORCED, EXTRUSION GRADE ACRYLONITRILE BUTADIENE STYRENE (ABS)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Filled • Good Dimensional Stability	• High Stiffness • High Strength	
Uses	• Consumer Applications • Electrical/Electronic Applications	• Household Goods • Industrial Applications	• Industrial Parts
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Molding Shrinkage - Flow	1.0E-3 to 2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	900000	psi	ASTM D638
Tensile Strength	10000	psi	ASTM D638
Tensile Elongation (Yield)	1.8	%	ASTM D638
Flexural Modulus	850000	psi	ASTM D790
Flexural Strength	15000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.3	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	200	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0	hr
Processing (Melt) Temp	460 to 500	°F
Mold Temperature	150 to 180	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

