

LAPEROS® A130

Polyplastics - Liquid Crystal Polymer

General Information

Product Description

High Strength, High Toughness

GF Reinforced

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• High Strength • High Toughness
UL File Number	• E106764
Part Marking Code (ISO 11469)	• >LCP-GF30<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm ³	ISO 1183
Molding Shrinkage ²			Internal Method
Across Flow : 0.0394 in	0.45	%	
Flow : 0.0394 in	0.010	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	30500	psi	ASTM D638
Tensile Elongation (Break)	2.2	%	ASTM D638
Flexural Modulus	2.18E+6	psi	ISO 178
Flexural Stress	39200	psi	ISO 178
Flexural Strain	3.0	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	17	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	85		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	464	°F	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
0.0394 in	1100	V/mil	
0.118 in	610	V/mil	
Relative Permittivity			IEC 60250
1 kHz	4.10		
1 MHz	3.70		
Dissipation Factor			IEC 60250
1 kHz	0.020		
1 MHz	0.020		
Arc Resistance	137	sec	ASTM D495
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94



Additional Information	Nominal Value	Unit	Test Method
Color Number	VF2001/BK010P		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 80x80x1 mm, 60 MPa Injection Pressure

