

LASTILAC SP G/17LATI INDUSTRIA TERMOPLASTICI SPA - *Acrylonitrile Butadiene Styrene***General Information****Product Description**

Compound based on Acrylonitrile-Butadiene-Styrene copolymer (ABS). Glass fibres. High dimensional stability. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber		
Features	• PFAS Free		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.18	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.30 to 0.50	%	
Flow : 0.0787 in	0.20 to 0.40	%	
Water Absorption ³ (Saturation, 73°F)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	870000	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	10200	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	1.9	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	1.9	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	7.1	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	212	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	203	°F	ISO 75-2/A
Vicat Softening Temperature	212	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.9E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	4.2E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	510	V/mil	ASTM D149
Comparative Tracking Index ⁴ (Solution A)	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

⁴ Without surfactant

