

LATAMID SP1

LATI INDUSTRIA TERMOPLASTICI SPA - *Polyamide*

General Information

Product Description

Product made of Special polyamide. Unfilled. High stiffness. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• PFAS Free		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.07	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	1.0 to 1.4	%	
Flow : 0.0787 in	1.0 to 1.4	%	
Water Absorption ³ (Saturation, 73°F)	2.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	348000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	9430	psi	ISO 527-2/5
Tensile Stress (Break, 73°F)	10200	psi	ISO 527-2/5
Tensile Strain (Yield, 73°F)	4.5	%	ISO 527-2/5
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.1	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	347	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	149	°F	ISO 75-2/A
Vicat Softening Temperature	338	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	7.5E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	7.5E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	560	V/mil	ASTM D149
Comparative Tracking Index ⁴ (Solution A)	600	V	IEC 60112

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

⁴ without surfactant

