

## LONGLITE® PBT 7330H-104

Chang Chun Plastics Co., Ltd. (CCP Group) - Acrylonitrile Butadiene Styrene + PBT

### General Information

#### Product Description

PBT/ABS 7330H-104 is a 30% glass fiber reinforced black color injection molding grade.

#### General

|                        |                                     |          |                 |
|------------------------|-------------------------------------|----------|-----------------|
| Material Status        | • Commercial: Active                |          |                 |
| Availability           | • Asia Pacific                      | • Europe | • North America |
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight |          |                 |
| Appearance             | • Black                             |          |                 |
| Processing Method      | • Injection Molding                 |          |                 |

### Properties <sup>1</sup>

| Physical                                                | Nominal Value | Unit                  | Test Method |
|---------------------------------------------------------|---------------|-----------------------|-------------|
| Density                                                 | 1.40          | g/cm <sup>3</sup>     | ISO 1183    |
| Molding Shrinkage                                       |               |                       | ISO 294-4   |
| Across Flow                                             | 0.50 to 1.1   | %                     |             |
| Flow                                                    | 0.10 to 0.30  | %                     |             |
| Mechanical                                              | Nominal Value | Unit                  | Test Method |
| Tensile Modulus (73°F)                                  | 1.19E+6       | psi                   | ISO 527-1   |
| Tensile Stress (Break, 73°F)                            | 14500         | psi                   | ISO 527-2   |
| Tensile Strain (Break, 73°F)                            | 2.4           | %                     | ISO 527-2   |
| Flexural Modulus (73°F)                                 | 870000        | psi                   | ISO 178     |
| Flexural Stress (73°F)                                  | 20300         | psi                   | ISO 178     |
| Impact                                                  | Nominal Value | Unit                  | Test Method |
| Charpy Notched Impact Strength (73°F)                   | 4.8           | ft·lb/in <sup>2</sup> | ISO 179/1eA |
| Thermal                                                 | Nominal Value | Unit                  | Test Method |
| Deflection Temperature Under Load (264 psi, Unannealed) | 320           | °F                    | ISO 75-2/A  |
| Melting Temperature                                     | 437           | °F                    | ISO 11357-3 |
| Electrical                                              | Nominal Value | Unit                  | Test Method |
| Surface Resistivity                                     | 1.0E+13       | ohms                  | IEC 60093   |
| Volume Resistivity                                      | 1.0E+14       | ohms·cm               | IEC 60093   |
| Electric Strength (0.0787 in)                           | 580           | V/mil                 | IEC 60243-1 |
| Flammability                                            | Nominal Value | Unit                  | Test Method |
| Flame Rating                                            | HB            |                       | UL 94       |
| Fill Analysis                                           | Nominal Value | Unit                  | Test Method |
| Melt Viscosity (500°F)                                  | 220           | Pa·s                  | ISO 11443   |

### Processing Information

| Injection              | Nominal Value | Unit |
|------------------------|---------------|------|
| Drying Temperature     | 248 to 284    | °F   |
| Drying Time            | 4.0           | hr   |
| Processing (Melt) Temp | 464 to 518    | °F   |
| Mold Temperature       | 140 to 212    | °F   |

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

