

Plaslube® ABS 8015 CL

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Copolymer
Appearance	• Clear/Transparent • Colors Available
Forms	• Pellets
Processing Method	• Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.08		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7400	psi	ASTM D638
Tensile Elongation (Yield)	6.0	%	ASTM D638
Flexural Modulus	340000	psi	ASTM D790
Flexural Strength	11400	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
32°F, 0.125 in	0.90	ft-lb/in	
73°F, 0.125 in	2.0	ft-lb/in	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	194	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	181	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

