

Plaslube® ABS E

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• High Viscosity
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Blow Molding • Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.03		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	0.30	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5400	psi	ASTM D638
Tensile Elongation (Break)	3.1	%	ASTM D638
Flexural Modulus	340000	psi	ASTM D790
Flexural Strength	10300	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°F, 0.125 in	2.1	ft·lb/in	
32°F, 0.125 in	2.8	ft·lb/in	
73°F, 0.125 in	5.7	ft·lb/in	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	201	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	178	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

