

Plaslube® Endura Control

Techmer Polymer Modifiers - *Polyamide*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• High Heat Resistance
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.10		ASTM D792
Molding Shrinkage - Flow (0.125 in)	9.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11600	psi	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	348000	psi	ASTM D790
Flexural Strength	13000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	3.8	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	275	°F	ASTM D648
Melting Temperature	320	°F	
CLTE - Flow	3.1E-5	in/in/°F	ASTM D696

Notes

¹ Typical properties: these are not to be construed as specifications.

