

Plaslube® LDPE E FR V-2

Techmer Polymer Modifiers - *Low Density Polyethylene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Flame Retardant
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.17		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	2900	psi	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Flexural Modulus	120000	psi	ASTM D790
Flexural Strength	4100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.0	ft-lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-1		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

