

Plaslube® PA12 TS18

Techmer Polymer Modifiers - *Polyamide 12*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• PTFE Lubricant: 18% • Silicone Lubricant: 2%
Features	• Lubricated
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	8500	psi	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	240000	psi	ASTM D790
Flexural Strength	10000	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.080		
vs. Steel - Static	0.060		
Wear Factor	6.0	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.70	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	270	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	172	°F	ASTM D648
CLTE - Flow	7.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	650	V/mil	ASTM D149

