

Plaslube® PA6/6 TL10 BK

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• PTFE Lubricant
Features	• Lubricated
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.19		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3 to 0.010	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	420000	psi	ASTM D638
Tensile Strength (Yield)	10300	psi	ASTM D638
Tensile Strength (Break)	10100	psi	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.60	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	490 to 530	°F
Middle Temperature	500 to 540	°F
Front Temperature	510 to 550	°F
Nozzle Temperature	515 to 555	°F
Processing (Melt) Temp	495 to 555	°F
Mold Temperature	125 to 225	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

Notes

¹ Typical properties: these are not to be construed as specifications.

