

Plaslube® PA6/6 TS15 BK

Techmer Polymer Modifiers - *Polyamide 66*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Heat Stabilizer • Lubricant
Features	• Heat Stabilized • Lubricated • Wear Resistant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	9900	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	380000	psi	ASTM D790
Flexural Strength	13300	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.17		
vs. Steel - Static	0.11		
Wear Factor	12	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.80	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	No Break		ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	410	°F	ASTM D648
CLTE - Flow	1.5E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

