

Plaslube® TPX-HTN-000AA

Techmer Polymer Modifiers - *Polyamide*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• High Heat Resistance
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.019	in/in	ASTM D955
Water Absorption (24 hr)	2.3	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11300	psi	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	460000	psi	ASTM D790
Flexural Strength	21700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.8	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	320	°F	ASTM D648
Continuous Use Temperature	266	°F	ASTM D794
Melting Temperature	295	°F	
CLTE - Flow	4.1E-5	in/in/°F	ASTM D696

Notes

¹ Typical properties: these are not to be construed as specifications.

