

Radiflam® A RV250 AE 100 C NT

Radici Group High Performance Polymers - *Polyamide 66*

General Information

Product Description

PA66 flame retardant injection moulding grade. 25% glass fibre reinforced. Natural colour.

Suitable for parts requiring fire retardancy, medium stiffness and good mechanical resistance. Rated V-0 according to UL-94.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Medium Stiffness
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-GF25 FR(17+72)

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.62	--	g/cm ³	ISO 1183
Molding Shrinkage ²				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.40	--	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	3.7	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.90	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.52E+6	--	psi	ISO 527-1/1A/1
Tensile Stress (Break)	20300	--	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.0	--	%	ISO 527-2/1A/5
Flexural Modulus ³	1.41E+6	--	psi	ISO 178
Flexural Stress ³	30500	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (73°F)	21	--	ft·lb/in ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	428	--	°F	ISO 75-2/1Af
Vicat Softening Temperature	464	--	°F	ISO 306/B50
Melting Temperature ⁴	500	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity (500 V)	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.016 in)	V-0	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.04 in	1760	--	°F	
0.08 in	1760	--	°F	

Processing Information



Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.10	%
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 212	°F
Injection Rate	Moderate-Fast	

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 280°C Melt Temperature, 80°C Mold Temperature, 60 MPa Cavity Pressure
- ³ 0.079 in/min
- ⁴ 10°C/min

