

Radilon® A CF400W 333 BK

Radici Group High Performance Polymers - *Polyamide 66*

General Information

Product Description

PA66 40% carbon fiber reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts and components requiring very high mechanical properties: stiffness, dimensional stability, fatigue and creep resistance. The presence of carbon fibers also provides higher electrical and thermal conductivity.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Carbon Fiber, 40% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Creep Resistant • Electrically Conductive • Fatigue Resistant	• Heat Stabilized • High Dimensional Stability • High Stiffness	• Thermally Conductive
Agency Ratings	• EU 2011/65/EC		
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA66-CF40		

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.32	--	g/cm ³	ISO 1183
Water Absorption (Saturation, 73°F, 0.0787 in)	5.7	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	1.6	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	4.64E+6	3.19E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	36300	23200	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.3	1.5	%	ISO 527-2/1A/5
Flexural Modulus ²	3.63E+6	--	psi	ISO 178
Flexural Stress ²	56600	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	4.3	--	ft·lb/in ²	
73°F	5.2	6.2	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	31	--	ft·lb/in ²	
73°F	31	40	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	482	--	°F	ISO 75-2/Bf
Vicat Softening Temperature	464	--	°F	ISO 306/B50
Melting Temperature ³	500	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (500 V)	1.0E+2	1.0E+2	ohms·m	IEC 62631-3-1
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	< 0.39	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index (0.08 in)	1290		°F	IEC 60695-2-12



Processing Information

Injection	Dry Unit
Drying Temperature - Desiccant Dryer	176 °F
Drying Time - Desiccant Dryer	2.0 to 4.0 hr
Dew Point - Desiccant Dryer	< -4 °F
Suggested Max Moisture	0.10 %
Processing (Melt) Temp	536 to 572 °F
Mold Temperature	176 to 212 °F
Injection Rate	Moderate

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 10°C/min

